

In the Specification:

Please replace the paragraph beginning at line 13 of page 7 with the following amended paragraph:

Silicon carbide has a much closer crystal lattice match to Group III nitrides than does sapphire (Al_2O_3), which is a very common substrate material for Group III nitride devices. The closer lattice match may result in Group III nitride films of higher quality than those generally available on sapphire. Silicon carbide also has a very high thermal conductivity so that the total output power of Group III nitride devices on silicon carbide is, typically, not as limited by thermal dissipation of the substrate as in the case of the same devices formed on sapphire. Also, the availability of semi-insulating silicon carbide substrates may provide for device isolation and reduced parasitic capacitance. Appropriate SiC substrates are manufactured by, for example, Cree, Inc., of Durham, N.C., the assignee of the present invention, and methods for producing are described, for example, in U. S. Patent Nos. Re. 34,861; 4,946,547; 5,200,022; and 6,218,680, the contents of which are incorporated herein by reference in their entirety. Similarly, techniques for epitaxial growth of Group III nitrides have been described in, for example, U. S. Patent Nos. 5,210,051; 5,393,993; 5,523,589; and ~~5,292,501~~ 5,592,501, the contents of which are also incorporated herein by reference in their entirety.